



MOMENTIVE
performance materials

SCS2350

silicone elastomeric sealant

Product Description

SCS2350 silicone elastomeric sealant is a neutral cure silicone sealant useful on a wide variety of materials. SCS2350 is supplied as a paste and upon cure produces a durable silicone rubber seal.

Typical Performance Properties

- **Silicone Durability** - cured silicone rubber exhibits long term resistance to natural weathering, including: ultraviolet radiation, high and low temperatures and rain and snow, with negligible change in elasticity.
- **Adhesion** - primerless adhesion to many substrates and finishes. May be considered a candidate for use with numerous construction-related materials, including: glass, polycarbonate, vinyl, numerous plastics, fluoropolymer and powder coated paints (including overspray, conversion-coated and anodized aluminum, ceramic and porcelain materials. Some finishes or substrates may require a primer.
- **±25% Movement Capacity** - can accommodate 25% movement in both extension and compression and has excellent recovery after cycling.
- **Faster Curing** - shortened work life to allow quicker handling time.
- **Good Workability** - temperature stable paste which is easily gunned and tooled under hot and cold conditions.
- **Thermal Stability (cured state)** - once properly cured, the material remains flexible over a range of -55°F (-48°C) to 300°F (121°C) and up to 400°F (177°C) under intermittent short term exposure.
- **Compatible** - with the following GE products: IGS3703, IGS3713-D1, IGS3723, IGS3743, SCS2000, SCS2700, SCS9000, SCS2800, SCS1800, SWS, SSG4000, SSG4000AC, SSG4800J, SSG4400, RGS7700.

Momentive Performance Materials is an exclusive licensee of General Electric. The company provides versatile materials as the starting point for our creative approach to ideas that help enable new developments across hundreds of industrial and consumer applications. We are helping cus-

tomers solve product, process, and performance problems; our silanes, fluids, elastomers, sealants, resins, adhesives, urethane additives, and other specialty products are delivering innovation in everything from car engines to biomedical devices. From helping to develop safer tires and

keeping electronics cooler, to improving the feel of lipstick and ensuring the reliability of adhesives, our technologies and enabling solutions are at the frontline of innovation.



Exclusive
Licensee

SCS2350 silicone elastomeric sealant

Basic Uses

- SCS2350 is useful as a weatherproofing material when sealing between dissimilar or similar materials in either new or remedial glazing / sealing applications.
- SCS2350 is useful as an internal frame sealant for curtainwall assembly.
- SCS2350 is useful as an adhesive in panel stiffener applications.

Packaging

SCS2350 is available in 10.1 fl. oz. (299 ml) plastic caulking cartridges.

Colors

SCS2350 sealant series is available in 3 standard colors:

Grade	Color
SCS2350.02	White
SCS2350.03	Black
SCS2350.09	Aluminum Grey

Limitations

SCS2350 silicone elastomeric sealant is not:

- For use underwater or when in continuous contact with water.
- Paintable. When paintability is desired, consider SCS7000.
- For use in Silicone Structural Glazing (SSG) Applications.
- For use on mirrors.
- For use on wet, damp, frozen or contaminated surfaces.

Technical Services

Additional technical information or literature may be available by contacting Momentive Performance Materials¹ at 1-800-255-8886.

Applicable Standards

SCS2350 silicone elastomeric sealant meets or exceeds the requirements of the following specifications:

American Society for Testing & Materials International.

- ASTM C920 Standard Specification for Elastomeric Joint Sealants; Type S, Grade NS, Class 25, Use A, G, O

Joint Designs and Dimensions

- Joint Movement - All moving joints should be designed so as not to allow three-sided adhesion of the sealant to occur. Three-sided adhesion hinders the ability of the sealant to extend and compress freely as desired and can lead to early joint failure (reference ASTM C1193 Standard Guide for Use of Joint Sealants).
- Joint Width - When using SCS2350 in a butt joint application, a minimum width of 1/4" is recommended and the sealant profile is best when cast in an hourglass shape with the depth of the sealant over the crown of the backer rod between 1/8" and 3/8".

Joint Designs and Dimensions

Backer materials, typically backer rod, provide the following benefits to aide in the correct application of SCS2350 silicone elastomeric sealant.

- To control and provide the desired sealant depth.
- Create a formed joint cavity that allows for the desired hourglass sealant shape.
- Provide a firm backup which helps attain full wetting of the substrates when the sealant is tooled.
- Act as a bond breaker to eliminate adhesion on the backside of a joint (three-sided adhesion).

SCS2350 silicone elastomeric sealant

Specifications

Typical property values of SCS2350 silicone elastomeric sealant as supplied and cured are set forth in the tables below. Typical product data values should not be used as specifications.

Typical Properties – Supplied

Property	Value	Test Method
Consistency	Paste	N/A
Polymer	100% Silicone	N/A
VOC	2.20 wt.%	WPSTM C1454
Work Life (tooling time)	15 minutes	N/A
Tack Free Time (@ 73°F, 50% RH)	1-2 hours	ASTM C679
Sag/Slump	0.1" max.	ASTM D2202

Typical Properties – Cured

Property	Value ⁽¹⁾	Test Method
Hardness	30 (+/-3)	ASTM D2240
Peel Strength		
(21-day cure @ 73°F (23°C) 50% RH)	>35 pli	ASTM C794
Movement Capability	±25%	ASTM C719
Service Temperature Range (after cure)	-55°F to +250°F (-48°C to 121°C)	N/A
Application Temperature Range	+40°F to +122°F (4°C to 50°C)	N/A

(1) Average value. Actual value may vary.

Installation

Sealants may not adhere or maintain long-term adhesion to substrates if the surface is not prepared and cleaned properly before sealant application. IN ALL CASES THE APPLICATOR MUST CONFIRM THE ACCEPTIBILITY OF EACH SEALANT-SUBSTRATE COMBINATION WITH A SITE ADHESION TEST PRIOR TO PROCEEDING WITH PROJECT INSTALLATION. A Momentive Performance Materials primer may be selected to enhance sealant bonding on some difficult to adhere to substrates. Momentive Performance Materials¹ can provide information and suggestions to user upon request.

Surface Preparation

Glass, Metals Paints, Smooth Surfaces, etc.

- Smooth surfaces can be wiped clean using a rag dampened with a cleaning solvent (Isopropyl Alcohol is typically useful). Proceed by cleaning the surfaces using a rag wetted with solvent and immediately use a second clean rag to wipe the wet solvent from the surface before it evaporates. Repeat this procedure as necessary until no contaminants are visible on the second cleaning rag.
- All surfaces that are to receive sealant must be clean, dry and free of contaminants (such as moisture/frost, oils, concrete form release agents, old sealants, asphalt and other surface treatments, etc.) to allow for optimal adhesion.

NOTE: When handling solvents, refer to manufacturer's MSDS for information on handling, safety and personal protective equipment.

SCS2350 silicone elastomeric sealant

Masking

Masking tape is recommended where appropriate to ensure a neat job and to protect adjoining surfaces from over-application of sealant. Masking tape should be removed immediately after tooling the sealant and before the sealant begins to skin over (tooling time).

Sealant Application

1. Cut tapered nozzle of caulking cartridge; suggest cutting nozzle at a 45° angle to assist in the dispensing & application of the sealant. The further down you cut, the bigger the opening and resulting bead size. Keep in mind that there is a 1/4" minimum contact surface of sealant required on all surfaces.
2. If applicable, puncture foil tip seal with nail and place cartridge in caulking gun.
3. Hold gun at a 45° angle to surface and squeeze trigger using even pressure.
4. Once sealant begins to dispense, move gun along at even pace. The sealant should fill the gap and touch both surfaces. The best bead is usually achieved by pushing the sealant out in a forward motion.
5. A tooling knife is then used to smooth the bead. Bead should be tooled within a few minutes of dispensing or before skin over (see typical properties for "tooling time").
6. Leave sealant undisturbed until sufficient cure.

Tooling

- Tool or strike the sealant with a concave tool applying light pressure to spread the material against the back-up material and the joint surfaces to ensure a void-free application.
- On sill applications, tool the sealant to shed water and to eliminate ponding.
- Tooling agents such as water, soap, or detergent solutions are not recommended.

SCS2350 silicone elastomeric sealant

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.momentive.com or, upon request, from any Momentive Performance Materials¹ representative. Use of other materials in conjunction with Momentive Performance Materials¹ products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Patent Status

Nothing contained herein shall be construed to imply the non existence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Emergency Service

Momentive Performance Materials¹ maintains an around-the-clock emergency service for its products. The American Chemistry Council (CHEMTREC), Transport Canada (CANUTEC), and the Chemical Emergency Agency Service also maintain an around-the-clock emergency service for all chemical products:

Location	GE Branded Products	All Chemical Products
Mainland U.S., Puerto Rico	518.233.2500	CHEMTREC: 800.424.9300
Alaska, Hawaii	518.233.2500 (collect)	CHEMTREC: 800.424.9300
Canada	518.233.2500 (collect)	CANUTEC: 613.996.6666 (collect) or CHEMTREC: 800.424.9300
Europe, Middle East, Africa	+32.(0)14.58.45.45 (Belgium)	CHEMTREC: +1-703.527.3887 (collect)
Latin America, Asia/Pacific, all other locations worldwide	+518.233.2500	CHEMTREC: +1-703.527.3887 (collect)
At sea	Radio U.S. Coast Guard, which can directly contact Momentive Performance Materials ¹ at 518.233.2500	CHEMTREC at 800.424.9300

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

Principal Locations

Regional Information	Phone	Fax
North America		
World Headquarters 187 Danbury Road Wilton, CT 06897, USA	800.295.2392	607.754.7517
Latin America		
Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700 Brazil	+55.11.4534.9650	+55.11.4534.9660
Europe, Middle East, Africa and India		
GE Bayer Silicones GmbH & Co. KG Leverkusen Germany	00.800.4321.1000	
Pacific		
GE Toshiba Silicones 6-2-31 Roppongi Minato-ku Tokyo 106-8550 Japan	+81.3.3479.5361	+81.3.3479.5391
Customer Service Centers		
North America		
South Charleston, WV 25303, USA E-mail: cs-na.osi@ge.com	Specialty Fluids 800.523.5862	304.746.1654
	UA, Silanes, Resins, and Specialties 800.334.4674	304.746.1623
	RTV Products-Elastomers 800.332.3390	304.746.1623
	Sealants and Adhesives and Construction 877.943.7325	304.746.1654
Canada		
Toronto, Canada	Within Canada 800.668.4644	905.858.6687
	Outside Canada 905.858.5187	
Latin America		
Argentina and Chile	+54.23.2055.2857	+54.23.2055.2811
Brazil	+55.11.4534.9650	+55.11.4534.9660
Mexico and Central America	+52.55.5257.6042	+52.55.5257.6094
Venezuela, Ecuador, Peru, Colombia, and Caribbean	+58.212.902.5167	+58.212.902.5158
E-mail: csla.gesosi@ge.com		
Europe, Middle East, Africa and India		
GE Bayer Silicones GmbH & Co. KG E: ebusiness1.gebs@ge.com	00.800.4321.1000	
GE Specialty Materials (Suisse) Sàrl E: cs-eur.osi@ge.com	00.800.4321.1000	
Pacific		
Japan E-mail: helpdesk@getos.co.jp	+ 81.276.20.6182	
China	+ 86.800.820.0202	
Korea	+ 82.2.530.6400	
Singapore	+ 65.6220.7022	
Worldwide Hotline	800.295.2392	+607.786.8131
Worldwide Web	ge.com/silicones	

THE MATERIALS, PRODUCTS AND SERVICES OF THE BUSINESSES MAKING UP MOMENTIVE PERFORMANCE MATERIALS INC., ITS SUBSIDIARIES AND AFFILIATES, ARE SOLD SUBJECT TO MOMENTIVE PERFORMANCE MATERIALS INC.'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGEMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, MOMENTIVE PERFORMANCE MATERIALS INC. MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN MOMENTIVE PERFORMANCE MATERIALS INC. STANDARD CONDITIONS OF SALE, MOMENTIVE PERFORMANCE MATERIALS INC. BUSINESS AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Momentive Performance Materials Inc.'s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Momentive Performance Materials Inc.'s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Momentive Performance Materials Inc.'s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Momentive Performance Materials. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Momentive Performance Materials Inc. or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Copyright 2007 Momentive Performance Materials Inc., all rights reserved. *Trademark of Momentive Performance Materials Inc. GE is a registered trademark of General Electric. Note: E-mail addresses are temporary and will be changing.

161-017-00E-GL
CDS: DataSCS2350 (7/07)